

## Soudaflex 40FC

Revision: 5/04/2018

Page 1 from 2

### Technical data

Basis	Polyurethane
Consistency	Stable paste
Curing system	Moisture curing
Skin formation* (20°C / 65% R.H.)	Ca. 15 min
Curing speed * (20°C / 65% R.H.)	3 mm/24h
Hardness	40 ± 5 Shore A
Density	1,30 g/ml
Elastic recovery (ISO 7389)	> 80 %
Maximum allowed distortion	± 20 %
Max. tension (DIN 53504)	1,70 N/mm <sup>2</sup>
Elasticity modulus 100% (DIN 53504)	0,80 N/mm <sup>2</sup>
Elongation at break (DIN 53504)	700 %
Temperature resistance	-30 °C → 90 °C
Application temperature	5 °C → 35 °C

This information relates to fully cured product. (\*) these values may vary depending on environmental factors such as temperature, moisture, and type of substrates.

### Product description

Soudaflex 40FC is a high quality, neutral, elastic, 1-component construction joint and adhesive sealant based on polyurethane.

### Properties

- Very easy to apply
- Permanently elastic after curing
- Excellent resistance to UV radiation
- Very good adhesion on many materials
- Excellent resistance to many chemicals

### Applications

- All sealing and bonding applications in the building industry.
- Structural bondings in vibrating constructions.
- Sealing of shrinking joints in concrete floors.
- Bonding of roof tiles.

### Packaging

*Colour:* white, black, teak, grey, concrete grey, other colors on request

*Packaging:* 310 ml alu cartridge, 300 ml sausage, 600 ml sausage, other packaging on request

### Shelf life

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

### Substrates

*Substrates:* all usual building substrates, metals, polyesters, ...

*Nature:* clean, dry, free of dust and grease.

*Surface preparation:* Apply Primer 100 on porous substrates. Prepare non-porous surfaces with Soudal primer or cleaner (see Technical Data Sheet)

There is no adhesion on PE, PP, PTFE (Teflon®) and bituminous substrates. We recommend a preliminary adhesion and compatibility test on every surface.

### Joint dimensions

*Min. width for bonding:* 2 mm

*Min. width for joints:* 5 mm

*Max. width for bonding:* 10 mm

*Max. width for joints:* 30 mm

*Min. depth for joints:* 5 mm

Recommendation sealing jobs: joint width = 2 x joint depth.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.

---

## Soudaflex 40FC

---

**Revision: 5/04/2018****Page 2 from 2****Application method**

*Application method:* With manual- or pneumatic caulking gun.

*Cleaning:* Clean with White Spirit or Soudal Surface Cleaner immediately after use (before curing).

*Finishing:* With a soapy solution or Soudal Finishing Solution before skinning.

*Repair:* With the same material

**Liability**

The content of this technical data sheet is the result of tests, monitoring and experience. It is general in nature and does not constitute any liability. It is the responsibility of the user to determine by his own tests whether the product is suitable for the application.

**Health- and Safety Recommendations**

Take the usual labour hygiene into account. Consult label and material safety data sheet for more information.

**Remarks**

- Soudaflex 40FC is paintable with most waterbased paints, however due to the large number of paints and varnishes available we strongly suggest a compatibility test before application.
- Soudaflex 40FC has a good UV resistance but can discolour under extreme conditions or after very long UV exposure.
- It is recommended to do a compatibility test prior to application.
- Contact with bitumen, tar or other plasticizer releasing materials such as EPDM, neoprene, butyl, etc. is to be avoided since it can give rise to discolouration and loss of adhesion.
- Do not apply or cure in the presence of uncured silicone sealants, alcohol or other solvent cleaners.
- When using different reactive joint sealants, the first joint sealant must be completely hardened before the next one is applied.

**Environmental clauses****Lead regulation:**

Soudaflex 40FC conforms to the requirements of LEED. Low –Emitting Materials: Adhesives and Sealants. SCAQMD rule 1168. Complies with USGBC LEED 2009 Credit 4.1: Low-Emitting Materials – Adhesives & Sealants concerning the VOC-content.

Remark: This technical data sheet replaces all previous versions. The directives contained in this documentation are the result of our experiments and of our experience and have been submitted in good faith. Because of the diversity of the materials and substrates and the great number of possible applications which are out of our control, we cannot accept any responsibility for the results obtained. Since the design, the quality of the substrate and processing conditions are beyond our control, no liability under this publication is accepted. In every case it is recommended to carry out preliminary experiments. Soudal reserves the right to modify products without prior notice.